

Bona Traffic HD™

Technical data sheet

Bona Traffic HD™ is for hardwood floor owners with an uncompromising attitude towards durability, being green and looking beautiful. When the wood matters - Bona Traffic HD™.

- Significantly outperforms all urethane finishes, including Bona Traffic®, in durability at 24 hours
- Unsurpassed scuff, scratch and chemical resistance at full cure
- Very low VOCs - less than 125
- Very low odor
- Clear and colorless, which highlights the true color of stained or natural wood floors. Will not change color over time, allowing for easy touch-up
- GREENGUARD Indoor Air Quality Certified®
- No sealer needed over a stained floor
- Exceptional build with excellent flow and leveling
- Available in Commercial Satin, Commercial Semi-Gloss, and Commercial Extra Matte
- Fast drying – approximately 2-3 hours
- Nonflammable with a non-offending odor
- Water clean-up

Technical data

Physical Characteristics:

Ingredients – Water, Polymer(s), and amorphous silica

Color – Milky white (wet)

pH – 7.9

Solids – 34% (with hardener)

Density – 8.70 lbs./gallon (1.04 S.G.)

US Regulatory VOC Compliant – 125 g/L (with hardener)

Coefficient of Friction - = 0.5

Gloss Level – (60°) – 7-10 for Commercial Extra Matte, 15-20 for Commercial Satin,

40-45 for Commercial Semi-Gloss

Odor – Very slight non-offensive odor

Stability – 1 year shelf life in unopened container

Packaging – 1-gallon plastic bottle

Application Characteristics:

Clarity – Clear and colorless when dry

Leveling – Excellent

Defoaming – Excellent

Drying Time – 2-3 hours

Pot Life – THE FINISH/HARDENER MIXTURE MUST BE USED WITHIN 4 HOURS AFTER IT IS MIXED. Product properties are diminished after 4 hours. The finish and hardener can only be mixed one time.

Coverage – 350-400 square feet per gallon

Percent Cured After 24 Hours – 80%, **72 hours** – 90%

Maximum Cure – 100% after 1 week

Recommended Use

Commercial and residential use including shopping malls, restaurants, offices, retail stores, theater stages, hospitals, schools, and nursing homes

Directions

BEFORE USING, READ ALL DIRECTIONS AND MATERIAL SAFETY DATA SHEETS.

FOR TECHNICAL ADVICE: Call Bona US at 800/872-5515

SANDING AND PREPARATION OF NEW FLOORS: 1. Sand and prepare floor using accepted industry association methods. 2. For a stained floor, make your final cut with 80-100 grit paper and screen to 80-100 grit. For an unstained floor, make your final cut with 80-100 grit paper and disc/screen to 120-150 grit. This burnishing will reduce the amount of grain raise. 3. Use a Tampico Brush on a buffer and vacuum thoroughly. 4. Tack with a dry Bona® Microfiber Mop or cloth. 5. Apply finish system.

THE BONA TRAFFIC HD™ FINISH SYSTEM: Apply a Bona sealer or Bona stain and 2 coats of Bona Traffic HD. Follow label directions. Adding a third coat of Bona Traffic Commercial is recommended in heavy-traffic commercial and residential areas. Visit www.bona.com for additional product information.

RECOMMENDED APPLICATORS: Bona® Floor Coater, Bona® Roller, Bona® Cut-In pad.

NOTE: Use a clean applicator for sealer and a separate clean applicator for finish.

MIXING INSTRUCTIONS: SHAKE WELL BEFORE USING. DO NOT THIN. DO NOT ADD WATER. 1. Shake Bona Traffic finish (Part A) well for 30 seconds. 2. Add Bona Traffic Hardener (Part B) to finish

Finishing



Bona®

Bona Traffic HDTM

Technical data sheet



(Part A). One 10.38 oz. bottle of hardener will activate one gallon of finish. To mix finish amounts of less than one gallon, use a 1:11.33 ratio. **3.** Immediately shake mixture vigorously for 30-45 seconds. **4.** Insert supplied filter into bottle only after adding hardener. **5.** Let sit for 5-10 minutes before applying. BONA TRAFFIC CANNOT BE REHARDENED.

FINISHING: **1.** Pour a 6" wide line of finish along the starting wall. Go with the grain of the wood. **2.** Using a pre-dampened applicator, draw the applicator forward with the grain of the wood, moving the finish toward the opposite wall. To maintain a wet edge at all times, hold the applicator at a snowplow angle. **3.** At the end of each run, turn the applicator towards you and pad out the applicator parallel to the wet edge. **4.** Feather out all turns. Do not push too hard or too fast to avoid drips flying off the applicator. **5. BE SURE YOU ARE USING THE RECOMMENDED COVERAGE OF 350-400 SQ. FT. PER GALLON. DO NOT SPREAD TOO THIN.** **6.** Allow the first coat to dry 2-3 hours. High humidity and/or low temperature conditions will extend the dry time (recommended conditions of 65-80° F/ 40-60% relative humidity). **7.** For smoothest results, abrade with a Bona[®] Conditioning Pad before applying final coat. Always vacuum and tack thoroughly with a slightly water dampened Bona Microfiber Mop or cloth after abrading. Allow final coat to dry at least 48 hours before use.

CAUTION! Do not recap finish/hardener mixture after 4 hours to avoid pressure build-up. Dispose of any remaining product in accordance with local, state and federal regulations. Decontaminate empty hardener (Part B) bottle prior to disposal by adding water to the one-quart line. Recap. Shake vigorously. Dispose of.

POT LIFE: THE FINISH/HARDENER MIXTURE MUST BE USED WITHIN 4 HOURS AFTER IT IS MIXED. Product properties are diminished after 4 hours. The finish and hardener can be mixed only one time.

INTERCOAT ABRASION: It is not necessary to abrade between Bona waterborne sealer and finish coats unless more than 48 hours has passed since the previous coat was applied. For smoothest results, abrade between all coats as necessary. When using solvent-based sealers, ALWAYS abrade before finish coats. Always vacuum and tack thoroughly with a slightly water-dampened Bona Microfiber Mop or cloth after abrading.

RECOATING:

BONA RECOAT SYSTEM: Guaranteed recoat system designed to safely remove all contaminants and prepare the floor surface for optimal adhesion of Bona Traffic HD[®]. See Bona Recoat System for application directions.

WHEN USING BONA PREP SYSTEM: Be sure floor is free from wax, polish and oily residues. Follow the Bona Prep[®] system, applying 1-2 coats of Bona Traffic HDTM finish. Delamination can occur if the Bona Prep process is not followed; always test for compatibility. NOTE: Bona Traffic HDTM will adhere to most stains and finishes after proper preparation and dry times. Stain, sealer and finish results may vary widely depending on the wood species, especially on oily and resinous Exotics. ALWAYS PREPARE A SAMPLE OR TEST AREA TO DETERMINE COMPATIBILITY, APPEARANCE AND DESIRED RESULTS.

Maintenance

CURING: The curing process takes approximately 7 days, (80% cured after 1 day, 90% after 3 days). Do not replace area rugs until the floor has fully cured. The floor may be walked on after 24 hours, but remains susceptible to scuffing or marring until completely cured. Furniture may be placed onto floor after 72 hours (90% cured). Do not drag or slide furniture. Use only a dry Bona Microfiber Mop or cloth for cleaning during the first week.

CLEAN-UP: Application tools should be cleaned with water and stored in an airtight container.

FLOOR CARE: Put walk-off mats at all entrance doorways to minimize dirt and grit. Sweep or vacuum daily and damp-wipe as needed with Bona[®] Professional Series Hardwood Floor Cleaner. Use felt pads under furniture legs and appliances.

STORAGE: Nonflammable - Bona Traffic and Hardener should be stored in a climate controlled environment. KEEP FROM FREEZING. Do not store above 100° F (38° C).

Order Information

Item #	Size	No./Case
WT155918001	1 Gallon – Extra Matte	2
WT155618001	1 Gallon – Satin	2
WT155318001	1 Gallon – Semi Gloss	2