



Malibu Dreams

# Malibu Amber

Complexity: **Moderate** | Topcoating: **Mega Gloss**  
 Brushing: **Optional** | Finish: **Glossy**

Ideal for a classic warm wood tone in your floor, sealed with glossy lacquer.

Malibu Amber applied on brushed white oak.  
 Results will vary depending on the colour and type of your original wood floor.

Products used
 <p>2x Bona Amber</p>
 <p>2x Bona Mega Gloss</p>

Directions	Drying time
1. Prepare the floor and end the sanding with grit 120.	
2. Apply Bona Amber using a roller or other suitable applicator (approx. 8-10 m <sup>2</sup> /lit).	1-2 h
3. Make a light intermediate abrasion to reduce any grain raise using Bona Diamond Abrasives grit 120. Vacuum or dust wipe.	
4. Apply another coat of Bona Amber.	1-2 h
5. Apply Bona Mega Gloss using a Bona Microfiber Roller 11 mm and let dry (approx. 8-10 m <sup>2</sup> /lit).	2-3 h
6. Apply a second coat of Bona Mega Gloss.	12-24 h

#### Other information

- Cleanliness is extra important when working with high gloss lacquers. A tip is to apply one coat of Mega Gloss with a stainless steel trowel prior to a final, roller applied, coat. This is an excellent clean up method.

#### Special considerations

A total of 4 coats is recommended to achieve a mirror like effect.

*This guide describes the overall treatment process of wooden floors and does not replace technical and safety datasheets, that are subject to change, and must be observed prior to use. The drying times suggested are typical drying times at 20°C/60% RH, and must be adjusted to local indoor climate conditions.*