

New Modern

# Modern Liquorice

Complexity: **Easy** | Topcoating: **Traffic HD SM**  
Brushing: **Required** | Finish: **Silk matte shine**

Floor brushed and painted black, with natural wood grains brought out beautifully.

*Modern Liquorice applied on brushed white oak.  
Results will vary depending on the colour and type of your original wood floor.*



| Directions  | Drying time |
|---|-------------|
| 1. Sand and brush the floor using Bona's Connect Brushes or Bona Fiber Pads.  |             |
| 2. Shake the Classic UX can and add 5% of Bona Mix Colour Black. Shake again thoroughly.  |             |
| 3. Apply the pigmented Classic UX using a Bona Roller with 11 mm pile, achieving an application rate of approx. 8-10 m <sup>2</sup> /lit.   | 1-2 h       |
| 4. Make a light intermediate abrasion to reduce grain raise using a Bona Scrad Pad. Add a Scrad Wing if needed. Vacuum or dust wipe.  |             |
| 5. Apply a second coat of pigmented Classic UX in the same manner to achieve full coverage.   | 2-3 h       |
| 6. Within 24 hours from the previous application, apply a protective coat of Bona Traffic HD SM. Note: Do not sand on the final coloured layer, before the application of the top coat. | 12 h        |

#### Other information

- If desired, Traffic HD can be replaced with lesser wear resist lacquers such as Mega, Mega ONE or Domo.

#### Special considerations

Brushing is required so as to preserve some of the wood feeling in this look.

*This guide describes the overall treatment process of wooden floors and does not replace technical and safety datasheets, that are subject to change, and must be observed prior to use. The drying times suggested are typical drying times at 20°C/60% RH, and must be adjusted to local indoor climate conditions.*