



New Modern

# Modern Pale

Complexity: **Moderate** | Topcoating: **Traffic HD XM**  
 Brushing: **Optional** | Finish: **Extra matte**

For the look and feel of sanded wood, with white pigmentation to enhance the impression.

*Modern Pale applied on brushed white oak.  
 Results will vary depending on the colour and type of your original wood floor.*

Products used

<b>2x Bona White</b>

<b>1x Bona Traffic HD XM</b>

Directions	Drying time
1. Prepare the floor and end the sanding with grit 120.	
2. Apply Bona White using a roller or other suitable applicator following the direction of the wood (approx. 12 m <sup>2</sup> /lit).	1-2 h
3. Abrade to reduce grain raise using the Bona Diamond Abrasives grit 120.	
4. Apply a second coat of Bona White in the same manner.	2-3 h
5. Protect surface with Bona Traffic HD XM.	6-12 h
6. An additional coat of lacquer may be needed in high traffic areas.	

#### Other information

- For lower wear resistance requirements, another non-yellowing lacquer such as Bona Novia or Bona Traffic can be used.
- In high traffic areas, consider ending with two layers of Bona Traffic HD.
- Best White effect is obtained by ending with an extramatt lacquer. Traffic Natural can also be used as an alternative.

*This guide describes the overall treatment process of wooden floors and does not replace technical and safety datasheets, that are subject to change, and must be observed prior to use. The drying times suggested are typical drying times at 20°C/60% RH, and must be adjusted to local indoor climate conditions.*

#### Special considerations

Herring bone floors can be challenging to treat with tinted lacquer. Floors that are laid in falling lengths are best suited for this application.