

Maintenance Instructions

Below is a complete list of available maintenance instructions, along with abbreviations to help you identify and select the right treatment.


WH-C	Wood Hard Wax Oil Cleaning
WH-DC	Wood Hard Wax Oil Deep Cleaning
WH-P	Wood Hard Wax Oil Protecting
WH-RC	Wood Hard Wax Oil Recoating
WL-C	Wood Lacquered Cleaning
WL-DC	Wood Lacquered Deep Cleaning
WL-P	Wood Lacquered Protecting
WL-RC	Wood Lacquered Recoating
WO-C	Wood Oiled Cleaning
WO-DC	Wood Oiled Deep Cleaning
WO-P	Wood Oiled Protecting
WO-RC	Wood Oiled Recoating
WS-C	Wood Sport Cleaning
WS-DC	Wood Sport Deep Cleaning
WS-P	Wood Sport Protecting
WS-RC	Wood Sport Recoating
WD-DC	Wood Decking Deep Cleaning
WD-P	Wood Decking Protecting
WD-RC	Wood Decking Recoating

Cleaning Instructions

Hard Wax Oiled Wood Flooring

Part of the Bona Care Program

WH-C



Dry cleaning - loose dirt

- Vacuum or sweep floors on a regular basis using a Bona Dusting Pad to remove loose dirt.
- Remove spills and stains with Bona Spray Mop.



Cleaning (A)

Moist cleaning - Stubborn dirt

- Spray or mop floors with a solution of Bona Clean W10 and water (1 dl to 10 litres).
- Remove using a Bona Cleaning Pad.



Moist cleaning - Stubborn dirt

- Pour a solution of Bona Clean W20 and water (1 dl to 10 litres) into the machine tank.
- Attach a white pad to the machine.
- Clean using the minimum amount of solution and ensure there are no puddles on the floor.
- Replace the cleaning water frequently.




Deep Cleaning Instructions

Hard Wax Oiled Wood Flooring

Part of the Bona Care Program


WH-DC



© A.I.S.E.

For best results, we recommend using Bona DeepClean W in combination with our Bona PowerScrubber. If using Bona DeepClean W with other scrubbing machines, follow the manufacturer's instructions for preparation and operation.

- Attach white or red brushes to the Bona PowerScrubber.
- Fill the tank with 1 litre of Bona DeepClean W. Fill the remaining volume with 9 litres of water.
- Set the brush contact pressure to medium.
- Clean the floor in a systematic way. Ensure there are no puddles on the floor and remove any residual liquid immediately with a mop.
- After cleaning, place the machine on a water-resistant surface.



To remove stubborn scuff marks and ingrained dirt, set the machine to maximum pressure. When running at maximum pressure ensure the machine is constantly in motion and never use with dry brushes.

Warning: running at maximum pressure may damage some floors.

Tip!

For tough marks

- Dilute Bona DeepClean W with water (1:5 ratio) in a spray bottle
- Spray the area and wait for 3 minutes
- Scour using the Bona PowerScrubber


Deep Cleaning (B)

Protecting Instructions

Hard Wax Oiled Wood Flooring

Part of the Bona Care Program

WH-P



© A.I.S.E

A thin layer of Bona Hard Wax Oil protects surfaces and restores shine.



© A.I.S.E

- Sweep and clean the floor, as per processes A1 & B.
- Pour approx. 1 dl of Bona Wax Oil W onto the floor (1 litre covers approx. 50-80m²). Distribute using a buffing machine with a Bona Wool Pad attached. Add more Bona Wax Oil W as required.
- For best results, buff the floor once again with a clean, dry Bona Wool Pad.
- Allow the floor to dry for approx. 12 hours prior to use.



50-80 sqm/lit




Recoating Instructions

Hard Wax Oiled Wood Flooring

Part of the Bona Care Program

WH-RC



© A.I.S.E

Recoating adds an additional tough and protective layer of hard wax oil to the floor. It also removes scuff marks and superficial scratches, improves slip resistance and restores the overall surface appearance. Recoating periodically can greatly extend the lifetime of the floor.

- Remove loose dust/grit etc. using a vacuum cleaner, scissor mop or other dry cleaning method.
- Degrease and clean the surface thoroughly using the Bona PowerScrubber (green brushes) and Bona DeepClean W diluted in the tank (10%). Ensure there are no puddles of cleaning solution on the floor.
- Allow the surface to dry.
- Abrade the surface with Bona Diamond Abrasives grit 240. Attach the diamond abrasive to a Quattro or Multidisc with intermediate pads in between. Abrade corners and edges manually. Ensure the entire surface is completely sanded.
- Vacuum to remove loose sanding dust or wipe with a Bona Dusting Pad. Alternatively use the Bona PowerScrubber with clean water to remove fine dust.
- Using a Bona Microfiber Roller 5 mm, apply a thin, even coat of Bona Hard Wax Oil to the entire floor (20-24 m²/lit). Avoid accumulation of product. Apply following the direction of the grain where possible. Allow to dry for a minimum of 12 hours prior to resuming use.



© A.I.S.E



Recoating (D)

Equipment needed:

- Bona PowerScrubber equipped with green brushes
- Bona DeepClean W
- Bona FlexiSand equipped with Quattro or Multidisc Intermediate pads (for Diamond Abrasives)
- Diamond Abrasives grit 240
- Bona Dusting Pad

Note

Recoating is only recommended if the floor has previously been treated with Bona Hard Wax Oil and maintained with Bona Wax Oil W. In case of doubt, test the surface for compatibility prior to application to ensure satisfactory adhesion.