



Bona DriFast® Sealer

Oil-Modified Polyurethane Sanding Sealer

Fast drying, oil-modified sealer designed to penetrate and seal bare wood



Bona DriFast® is a quick drying, oil-modified polyurethane sanding sealer that is designed to penetrate and seal bare wood. It is compatible with all Bona® stains, oil-modified and waterborne finishes. It meets ASTM D 1640 for quick-dry sealers and is VOC compliant under U.S. EPA regulations.

- Fast drying – 1 ½ - 2 hours
- Coverage rate 600-700 sq.ft./gal
- Rapid hardness development
- Clean up with mineral spirits



Bona DriFast® Sealer

Oil-Modified Polyurethane Sanding Sealer

Fast drying, oil-modified sealer designed to penetrate and seal bare wood

PHYSICAL CHARACTERISTICS

Ingredients – Mineral spirits (solvent), urethane resins, silica, driers.

Color – wet – amber; dry – light amber

Solids – 37%

Density – 7.21 lbs/gallon (0.866 S.G.)

US Regulatory VOC – 550 g/L

Odor – Mineral spirits

Stability – Two-year shelf life in unopened container

Flash Point – 115° F (46° C)

Packaging – 1-gallon, 5-gallon pail

APPLICATION CHARACTERISTICS

Clarity – Clear

Leveling – Excellent

Defoaming – Excellent/complete

Drying Time – 1-1/2 - 2 hours

Coverage – 600-700 square feet per gallon

Percent Cured After 24 Hours – 60%

Maximum Cure – 2 weeks

RECOMMENDED USE

Formulated for use under all Bona® oil-modified and waterborne finishes.

BEFORE USING, READ ALL DIRECTIONS AND SAFETY DATA SHEETS.

FOR TECHNICAL ADVICE: Call Bona US at 800-872-5515

RESPONSE

Get medical attention if you feel unwell. IF INHALED: Remove victim to fresh air and keep at rest in a position comfortable for breathing. Call a POISON CENTER or physician if you feel unwell. IF SWALLOWED: Immediately call a POISON CENTER or physician. Do NOT induce vomiting. IF ON SKIN: Wash with plenty of soap and water. Take off contaminated clothing. If skin irritation occurs: Get medical attention.

COMPATIBILITY

Bona DRIFAST® Sealer will adhere to most stains after proper preparation and dry times. Stain, sealer, and finish results may vary depending on the wood species, especially on oily and resinous exotics. ALWAYS PREPARE A SAMPLE OR TEST AREA TO DETERMINE COMPATIBILITY IF USING ANYTHING OTHER THAN A BONA® PRODUCT.

SANDING AND PREPARATION OF NEW FLOORS

1. Sand and prepare floor using accepted industry association methods. 2. Make your final cut with either a screen or MultiDisc using 80 to 120-grit abrasives. 3. Use a Tampico Brush on a buffer and vacuum thoroughly. 4. Tack with dry Bona® Microfiber Mop or cloth to remove dust. 5. Apply Bona Sealer system.

THE BONA DRIFAST® SEALER SYSTEM

Apply 1 coat of Bona DriFast Sealer and 2 coats of a Bona waterborne or oil-modified finish. Bona DriFast Sealer minimizes sidebonding and grain raise, provides a build layer and prevents the finish from penetrating into the wood surface. Visit bona.com for additional product and application information.

RECOMMENDED APPLICATORS:

3/16" nap mohair roller, paint tray, natural bristle brush, T-bar, flocked foam paint pad. NOTE: Use a clean applicator for sealer and a separate clean applicator for finish.

MIXING INSTRUCTIONS

SHAKE AND STIR WELL BEFORE USING! DO NOT THIN.



Bona DriFast® Sealer

Oil-Modified Polyurethane Sanding Sealer

Fast drying, oil-modified sealer designed to penetrate and seal bare wood

SEALING

1. Pour sealer into paint tray. Wet the 3/16" mohair roller.
2. Apply sealer to a 3'x3' section of the floor against the grain at a coverage rate of 600 – 700 square feet per gallon.
3. Without adding more sealer to roller, re-roll entire 3'x3' section with the grain of the wood.
4. Continue process throughout entire floor. Note: Apply evenly, excessive amounts of sealer may cause floor failure.
5. Allow sealer to dry thoroughly for a minimum of 2 hours under ideal conditions of 60-80°F (16°C-27° C)/ 35-75% relative humidity. High humidity and/or low temperature conditions will extend dry time while increased ventilation and airflow will reduce dry time.
6. Abrade Bona DriFast Sealer using 120-grit or finer, screen or 1-2 (stacked) Bona Conditioning Pads and 1-2 Bona Diamond 180 to 240-grit abrasives.
7. Thoroughly vacuum and dry tack with Bona Microfiber Tacking pads (or slightly dampened with water).
8. Apply a Bona® finish according to label directions.

CLEAN-UP

Clean applicator tools and equipment with mineral spirits.

STORAGE AND DISPOSAL

Store in a well-ventilated place. Keep cool. Keep container closed when not in use. Do not store above 100° F (38° C). Do not transfer contents to other containers for storage and disposal. In case of spillage, absorb with inert material. Dispose of contaminated absorbent, container, and unused contents in accordance with local, state and federal regulations.

DANGER

RAGS, STEEL WOOL OR WASTE SOAKED WITH DRIFAST® SEALER MAY SPONTANEOUSLY CATCH FIRE IF IMPROPERLY DISCARDED. IMMEDIATELY AFTER EACH USE, PLACE RAGS, STEEL WOOL OR

WASTE IN A SEALED, WATER-FILLED METAL CONTAINER.

ORDERING INFORMATION

Item #	Description	Size	No./Case	Weight (lbs.)
SB750051001	Bona DriFast Sealer	Quart	6	12.75
SB750018172	Bona DriFast Sealer	Gallon	4	32.7
SB750018173	Bona DriFast Sealer	5 Gallon	1	38.5