



Bona DriFast® Sealer

OIL-MODIFIED POLYURETHANE SANDING SEALER

Fast drying, oil-modified sealer designed to penetrate and seal bare wood



A fast drying, oil-modified sealer designed to penetrate and seal bare wood.

Bona DriFast® Sealer is a quick drying, oil-modified polyurethane sanding sealer that's designed to penetrate and seal bare wood. It is compatible with all Bona stains, oil-modified and waterborne finishes. It meets ASTM D 1640 for quick-dry sealers and is VOC Compliant under U.S. EPA regulations.

- Fast drying – 1½-2 hours
- Coverage rate 600-700 sqft/gal
- Rapid hardness development
- Cleans up with mineral spirits

Bona DriFast® Sealer

OIL-MODIFIED POLYURETHANE SANDING SEALER

Fast drying, oil-modified sealer designed to penetrate and seal bare wood

TECHNICAL DATA

Ingredients:	Mineral spirits (solvent), urethane resins, silica, driers
Solid Content:	37%
Density:	7.21 lbs/gallon (0.866 S.G.)
Flash Point:	115° F (46° C)
US Regulatory VOC:	550 g/L
Odor:	Mineral spirits
Color:	Amber, when wet. Light amber when dry.
Packaging:	1-gallon, 5-gallon pail
Shelf life:	Two-year shelf life in unopened container
Storage/Transport:	Store in a well-ventilated place. Keep cool. Keep container closed when not in use. Do not store above 100° F (38° C). Do not transfer contents to other containers for storage and disposal. In case of spillage, absorb with inert material.
Application Tools:	Bona® Heavy Weight T-bar, Lambswool applicator, natural bristle brush, cut-in pad and ¼" mohair roller. NOTE: Use a clean applicator for sealer and a separate clean applicator for finish.
Coverage:	600-700 square feet per gallon
Leveling:	Excellent
Defoaming:	Excellent
Drying time:	1-1/2 - 2 hours
Clean-up:	Clean application tools and equipment with mineral spirits.
Disposal:	Dispose of contaminated absorbent, container, and unused contents in accordance with local, state and federal regulations.

BEFORE USING, READ ALL DIRECTIONS AND SAFETY DATA SHEETS. FOR TECHNICAL ADVICE: Call Bona US at 800-872-5515

HAZARD WARNING: RAGS, STEEL WOOL OR WASTE SOAKED WITH DRIFAST® SEALER MAY SPONTANEOUSLY CATCH FIRE IF IMPROPERLY DISCARDED. IMMEDIATELY AFTER EACH USE, PLACE RAGS, STEEL WOOL OR WASTE IN A SEALED, WATER-FILLED METAL CONTAINER.

Bona DriFast® Sealer

OIL-MODIFIED POLYURETHANE SANDING SEALER

Fast drying, oil-modified sealer designed to penetrate and seal bare wood

RESPONSE

Get medical attention if you feel unwell. IF INHALED: Remove victim to fresh air and keep at rest in a position comfortable for breathing. Call a POISON CENTER or physician if you feel unwell. IF SWALLOWED: Immediately

call a POISON CENTER or physician. Do NOT induce vomiting. IF ON SKIN: Wash with plenty of soap and water. Take off contaminated clothing. If skin irritation occurs: Get medical attention.

RECOMMENDED USE

Formulated for use under all Bona® oil-modified and waterborne finishes.

COMPATIBILITY

Bona DRIFAST® Sealer will adhere to most stains after proper preparation and dry times. Stain, sealer, and finish results may vary depending on the wood species, especially

on oily and resinous exotics. ALWAYS PREPARE A SAMPLE OR TEST AREA TO DETERMINE COMPATIBILITY IF USING ANYTHING OTHER THAN A BONA® PRODUCT.

BONA PRODUCT SYSTEM

Apply 1 coat of Bona DriFast Sealer and 2 coats of a Bona waterborne or oil-modified finish. Bona DriFast Sealer minimizes sidebonding and grain raise, provides a build

layer and prevents the finish from penetrating into the wood surface. Visit bona.com for additional product and application information.

PREPARATION

1. Sand and prepare floor using accepted industry association methods. 2. Make your final cut with either a screen or MultiDisc using 80 to 120-grit abrasives. 3. Use a

Tampico Brush on a buffer and vacuum thoroughly. 4. Tack with dry Bona® Microfiber Mop or cloth to remove dust. 5. Apply Bona Sealer system.

MIXING INSTRUCTIONS

SHAKE AND STIR WELL BEFORE USING. DO NOT THIN.

Bona DriFast® Sealer

OIL-MODIFIED POLYURETHANE SANDING SEALER

Fast drying, oil-modified sealer designed to penetrate and seal bare wood

APPLICATION

1. Pour sealer into paint tray. Wet the 3/16" mohair roller. 2. Apply sealer to a 3'x3' section of the floor against the grain at a coverage rate of 600 – 700 square feet per gallon. 3. Without adding more sealer to the roller, re-roll the entire 3'x3' section with the grain of the wood. 4. Continue the process throughout the entire floor. Note: Apply evenly; excessive amounts of sealer may cause floor failure. 5. Allow sealer to dry thoroughly for a minimum of 2 hours under ideal conditions of 60-80°F (16°C-27° C)/ 35-75% relative humidity. High humidity and/or low temperatures will extend dry time, while increased ventilation and airflow will reduce it.

INTERCOAT ABRASION

It is recommended to abrade in between all coats of oil-modified sealers and finishes. For the smoothest results, abrade between coats as necessary using 120-grit or finer screen, conditioning pad, or 180- to 240-grit Diamond abrasive. Thoroughly clean abraded floor using Bona PowerScrubber® (water only) OR vacuum and tack with Bona Microfiber Cleaning Pads (dry or slightly dampened with water).

Bona US
24 Inverness Place East, Suite 100
Englewood, Co. 80112